



Cham Paper Group

Technical Data Sheet

Name ADICAR OGR

Structure



Features

- One side double coated kraft paper with reverse side coat
- Calendered (super calendered)
- Oil and grease treatment without PFOA and PFOS
- Excellent oil and grease barrier (Kit Test)
- Good results in letterpress, flexo and offset printing
- Application: labelling of tyres as well as greasy foodstuff like meat

Specifications

Target values at 23°C / 50% R.H. for general guidance only	Methods	Units			
Substance	ISO 536	g/m ²	70.0	80.0	90.0
Thickness	ISO 534	µm	64.0	75.0	84.0
Brightness R457	DIN 53145	%	84.0	84.0	84.0
Opacity	ISO 2471	%	84.0	86.0	88.0
Gloss Lehmann 75° top side	ISO 8254-1	%	57.0	57.0	56.0
Roughness PPS H10 reverse side	ISO 8791-4	µm*100	140.0	140.0	150.0
Tensile strength MD	ISO 1924	N/15mm	68.0	74.0	86.0
Tensile strength CD	ISO 1924	N/15mm	40.0	45.0	48.0
Kit test top side	TAPPI UM 559	Nr.	8.0	8.0	8.0
Kit test reverse side	TAPPI UM 559	Nr.	6.0	6.0	6.0

Edition: November 13

Important: The information given is based on our best knowledge at the time of printing. It is given in good faith and represents neither implied nor actual guarantee and no legal warranty for specific properties or for suitability for a specific application. Responsibility for testing the suitability of the product for specific applications lies with the purchaser. We shall be pleased to aid customers with such tests where possible. Should a claim be taken into consideration, liability will, under no circumstances exceed the value of the goods supplied. Cham guarantees the impeccable quality of its goods in accordance with agreed specifications and their standard conditions of sale and delivery.