



Cham Paper Group

Technical Data Sheet

Name **ADICAR STAMP**

Structure



Features

- One side double coated kraft paper with reverse side coat
- Calendered (super calender)
- Excellent lay flat properties
- Excellent properties for rotogravure printing
- Without OBA
- Application: self adhesive post stamps
- Conformity: BfR (German Federal Institute for Risk Estimation)

Specifications

Target values at 23°C / 50% R.H. for general guidance only	Methods	Units	Provisional	Provisional	Provisional	provisional
Substance	ISO 536	g/m ²	80.0	90.0	100.0	130.0
Thickness	ISO 534	µm	70.0	80.0	90.0	120.0
Brightness R457	DIN 53145	%	85.0	85.0	85.0	85.0
Opacity	ISO 2471	%	86.0	88.0	90.0	93.0
Gloss Lehmann 75° coated side	ISO 8254-1	%	60.0	60.0	60.0	60.0
Roughness PPS H10 coated side	ISO 8791-4	µm*100	110.0	110.0	120.0	120.0
Roughness PPS H10 reverse side	ISO 8791-4	µm*100	280.0	280	280	280
Tensile strength MD	ISO 1924	N/15mm	72.0	81.0	87.0	115.0
Tensile strength CD	ISO 1924	N/15mm	43.0	48.0	58.0	68.0
Cobb test coated side	ISO 535	g/m ²	29.0	29.0	29.0	30.0
Cobb test reverse side	ISO 535	g/m ²	31.0	31.0	31.0	31.0
Absolute humidity	ISO 287	%	4.5	4.5	4.5	4.5

Edition: May 14

Important: The information given is based on our best knowledge at the time of printing. It is given in good faith and represents neither implied nor actual guarantee and no legal warranty for specific properties or for suitability for a specific application. Responsibility for testing the suitability of the product for specific applications lies with the purchaser. We shall be pleased to aid customers with such tests where possible. Should a claim be taken into consideration, liability will, under no circumstances exceed the value of the goods supplied. Cham guarantees the impeccable quality of its goods in accordance with agreed specifications and their standard conditions of sale and delivery.