



Cham Paper Group

Technical Data Sheet

Name CARCOAT SOFT

Structure



Features

- One side double layer clay coated kraft paper back side pigmented
- High calendered (super calender)
- Good flatness and rigidity
- Consistent runnability
- Excellent results in rotogravure and flexo printing
- Application: Outside soft wrapping, cigarettes, chocolate, etc.

Specifications

Target values at 23°C / 50% R.H. for general guidance only	Methods	Units	
Substance	ISO 536	g/m ²	125.0
Thickness	ISO 534	µm	107.0
Brightness R457	DIN 53145	%	83.0
Opacity	ISO 2471	%	92.0
Gloss Lehmann 75° top side	ISO 8254-1	%	84.0
Roughness PPS H10 top side	ISO 8791-4	µm*100	100.0
Tensile strength MD	ISO 1924	N/15mm	110.0
Tensile strength CD	ISO 1924	N/15mm	65.0
Absolute humidity	ISO 287	%	4.5

Edition: November 13

Important: The information given is based on our best knowledge at the time of printing. It is given in good faith and represents neither implied nor actual guarantee and no legal warranty for specific properties or for suitability for a specific application. Responsibility for testing the suitability of the product for specific applications lies with the purchaser. We shall be pleased to aid customers with such tests where possible. Should a claim be taken into consideration, liability will, under no circumstances exceed the value of the goods supplied. Cham guarantees the impeccable quality of its goods in accordance with agreed specifications and their standard conditions of sale and delivery.